

TE-E110

10oz ENVIRONMENTAL NONWOVEN GEOTEXTILE



Titan has provided the containment and erosions control industries with the highest quality geotextiles available. Our nonwoven needle punched geotextiles are manufactured using polypropylene fibers, which are formed into a dimensionally stable network which allows the fibers to maintain their relative position. These products resist ultraviolet deterioration, rotting, biological degradation, and are inert to commonly encountered soil chemicals.

TESTED PROPERTY	TEST METHOD	UNIT ENGLISH (METRIC)	VALUE ENGLISH (METRIC)
Weight	ASTM D 5261	oz/yd ² (g/m ²)	10.0 (339)
Tensile Strength (Grab)	ASTM D 4632	lbs (N)	270 (1201)
Elongation	ASTM D 4632	%	50
Trapezoid Tear	ASTM D 4533	lbs (N)	100 (444)
Thickness*	ASTM D 5199	mils (mm)	105 (2.7)
CBR Puncture Resistance	ASTM D 6241	lbs (N)	725 (3225)
U.V. Resistance	ASTM D 4355	%/hrs	70/500
Apparent Opening Size (AOS)	ASTM D 4751	U.S. Sieve (mm)	100 (0.150)
Permittivity*	ASTM D 4491	sec ⁻¹	0.94
Permeability*	ASTM D 4491	cm/sec	0.3
Water Flow*	ASTM D 4491	gpm/ft ² (l/min/m ²)	75 (3055)
TYPICAL ROLL DIMENSIONS			
Roll Dimensions		ft	15 x 300
Roll Area		yd ²	500
Estimated Roll Weight		lbs	312.5

NOTES:

*At time of manufacturing. Handling may change these properties.

This data is provided for informational purposes only. Titan makes no warranties as to the suitability or the fitness for a specific use or merchantability of the products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check with us for current updates.

TITAN ENVIRONMENTAL USA

Tel: 1-713-849-1311 | Email: info@titanenviro.com | Web: www.titanenvirousa.com

(Rev. March, 2018)

TRUST. QUALITY. VALUE