

TITAN 30mil LLDPE

SMOOTH GEOMEMBRANE



Titan's 30mil polyethylene is produced from virgin polyethylene resins. It has outstanding flexibility and elongation characteristics. Titan's 30mil Polyethylene contains approximately 97.5% polymer and 2.5% carbon black, anti-oxidants and heat stabilizers, and contains no additives, fillers or extenders. Titan's 30mil Polyethylene does not contain plasticizers which can migrate to the surface, causing premature aging. Manufactured from virgin polyethylene resins, it is designed to provide a high quality, economical Geomembrane.

TESTED PROPERTY	TEST METHOD	UNIT ENGLISH (METRIC)	VALUE ENGLISH (METRIC)
Thickness	ASTM D 5199	mil (mm)	30 ± 10% (0.75)
Density	ASTM D 1505	g/cm ³	0.920
Tensile Strength – Strength at Break	ASTM D 6693	lb/in-width (kN/m)	114 (20)
Tensile Strength – Elongation at Break	ASTM D 6693	%	850
Tear Resistance	ASTM D 1004	lb (N)	16 (71)
Puncture Resistance	ASTM D 4833	lb (N)	46 (205)
Dimensional Stability	ASTM D 1204	%	±2
Carbon Black Content	ASTM D 1603	%	> 2.0 / > 3.0
Hydrostatic Resistance	ASTM D 751	kPa	1206
U.V. Resistance GRI-GM-11	ASTM D 5885	%	35
Low Temp. Impact Failure	ASTM D 746	°F	< -94
Shop Shear Seam Strength	ASTM D 4437	lb/in (kN/m)	42 (7.3)
Shop Peel Seam Strength	ASTM D 4437	lb/in (kN/m)	35 (6.1)

This data is provided for informational purposes only. Titan makes no warranties as to the suitability or the fitness for a specific use or merchantability of the products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check with us for current updates.

TITAN ENVIRONMENTAL USA

Tel: 1-713-849-1311 | Email: info@titanenviro.com | Web: www.titanenvirousa.com

(Rev. April, 2018)

TRUST. QUALITY. VALUE