

Titan RCG-20

20 mil WOVEN COATED GEOMEMBRANE



Commonly used for interim landfill covers and short-term liners. Titan RCG-20 is a medium weight fabric incorporating a coating designed to improve toughness and abrasion resistance, and is intended for exposed applications up to 5 years.

PRODUCT SPECIFICATIONS:

Weave: Woven black HDPE scrim
Coating: LLDPE 2.5 mil average each side (60g/m²/side)
Colour: White, black or other colored coatings available
Weight 9.0 oz/yd² (305/m²) ± 5%

PERFORMANCE PROPERTIES:

The following data are typical values based on ASTM standard tests. This data should not be considered specification.

Thickness ASTM D1777	Nominal 20 mil (0.40 mm), ± 10%
Grab Tensile (N) ASTM D7004	MD 250 lb (1110) TD 340 lb (1510)
Strip Tensile (N/5cm) ASTM D7003	MD 175 lb/in (1554) TD 270 lb/in (2398)
Tongue Tear—large scale (N) ASTM D5884	MD 75 lb (333) TD 75 lb (333)
Mullen Burst ASTM D751	550 psi (2584 kPa)
MVTR ASTM E96 Proc. BW	0.40 g/m ² -24hr (0.06 perms)
Hydraulic Conductivity (Permeability) Calculated from MVTR	1.97 x 10 ⁻¹² cm/s
Hydrostatic Resistance ASTM D751	139 psi (958 kPa)
Puncture Resistance ASTM D4833	140 lb (622 N)
CBR Static Puncture ASTM D6241	973 lb (4320 N)
Carbon Black Content ASTM D4218	3 %
Dimensional Stability ASTM D1204	MD -4.3% TD -1.8%
Low Temperature Flex ASTM D2136-94	MD & TD: Pass @ -65°F (-85°C)
HP-OIT ASTM D5885 (Measured on coating formulation)	1684 minutes
Accelerated UV Weathering ASTM G151 ASTM G154	>90% strength retention after 2000 hours exposure @0.77 W/m ² /nm, or 1200 hrs exposure @1.35 W/m ² /mn

MD = Machine Direction. TD = Transverse Direction
 i Q.U.V [A-340 Lamps]; 8 hrs UV @ 60°C; 4 hrs condensation @ 50°C

These values are typical data and are not intended as limiting specifications.

This data is provided for informational purposes only. Titan makes no warranties as to the suitability or the fitness for a specific use or merchantability of the products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check with us for current updates.