

TE-FGP10

BI-AXIAL FIBERGLASS GEOGRID



Titan's TE-FGP fiberglass geogrid is specifically designed for asphalt reinforcement. Its optimal apertures allow asphalt particles to penetrate through the grid to achieve high interlock and effective bonding of the two asphalt lifts. This geogrid is also polymer coated which ensures proper adhesion to the asphalt layers over the tack coat surface, and further optimizes the chemical compatibility between the fiberglass reinforcement and the pavement overlay to create a solid bond of the asphalt layers over the tack coat surface. This bond ensures that the reinforcing grid is in a position to effectively accept and distribute tensile stresses.

It is self-adhesive and offers excellent heat resistance; minimal shrinkage at high temperatures; high chemical, physical and biological durability along with optimal elastic modulus and aperture size. It is biologically unaffected by soil micro-organisms, inert to all chemicals normally found in the soil, and formulated to resist ultraviolet degradation.

TESTED PROPERTY	TEST METHOD	UNIT ENGLISH (METRIC)	VALUE ENGLISH (METRIC)	
			MD	XD
Ultimate Tensile Strength	ASTM D 6337	lb/inch (kN/m)	571 (100.0)	571 (100.0)
Tensile Strength at 2% strain ⁽¹⁾	ASTM D 6637	lb/inch (kN/m)	456 (80.0)	456 (80.0)
Secant Stiffness EA at 2% Strain ⁽¹⁾	ASTM D 6637	lb/inch (kN/m)	22,847 (4,000.0)	22,847 (4,000.0)
Shrinkage Properties	Internal Test Method	%	Less than 0.5% at 200°C after 15 minutes	
Strain at Ultimate ⁽²⁾	ASTM D 6637	%	<3	<3
Grid Material			Fiberglass Grid	
Coating			Polymeric with pressure sensitive self-adhesive backing	
Optimum Elasticity Modulus ⁽²⁾		psi (mPA)	10.6 x 10 ⁶ (73,000)	
Melting Point Coating	ASTM D 276	°F (°C)	>752 (>400)	
Melting Point Glass	ASTM C 338	°F (°C)	>1,508 (>820)	
Aperture Size (centre to centre of strand)	Nominal	inch (mm)	0.5 (12.7)	0.5 (12.7)
Mass/Unit Area ⁽²⁾	ASTM D 5261	oz/yd ² (g/m ²)	12.7 (420)	
STANDARD ROLL DIMENSIONS				
Roll Width ⁽³⁾⁽⁴⁾	Minimum	ft (m)	5.0 (1.5) or 7.38 (2.25)	
Roll Length ⁽³⁾⁽⁴⁾	Minimum	ft (m)	328.08 (100.0) or 246.06 (75)	

NOTES:

1. MARV – Minimum Average Roll Values
2. Mean
3. Minimum
4. Typical. The products may be fabricated to customer lengths to meet customer needs.

This data is provided for informational purposes only. Titan makes no warranties as to the suitability or the fitness for a specific use or merchantability of the products referred to, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability from resulting loss or damage. This information is subject to change without notice, please check with us for current updates.

TITAN ENVIRONMENTAL USA

Toll Free: 1-713-849-1311 | Email: info@titanenvirousa.com | Web: www.titanenvirousa.com

(Rev. April, 2019)

TRUST. QUALITY. VALUE